Tel.: +49 (0) 96 45 - 88 300 Fax: +49 (0) 96 45 - 88 390




S 900Interface Material



Graphite S 900 is a highly densed, natural graphite without binding material, which is rolled or pressed into films or plates. S 900 has exceptional qualities and is therefore used particularly as a cost-effective alternative to conventional interface material. Especially, the anisotropy of the thermal properties (coupled with a possible weight saving of up to 30% compared to conventional materials made of copper or aluminum), makes the S 900 interesting for headspreader applications.

In addition, applications in vacuum or even at high temperatures (400 °C) are possible. Graphite S 900 has no electrical insulation and can be customized and applied with an adhesive coating.

| Properties | Unit | S 900 |
|--------------------------------------|---------|-------------------|
| Colour | | black |
| Thermal Properties | | |
| Thermal resistance R _{th} | K/W | 0.08 |
| Thermal impedance R _{ti} | °Cmm²/W | 34 |
| | Kin²/W | 0.047 |
| Thermal conductivity λ z (x/y) | W/mK | 7.5 (> 300) |
| Electrical Properties | | |
| Breakdown voltage U _{d; ac} | kV | conductive |
| Electrical resistance z (x/y) | Ωμm | 700 - 800 (7 - 9) |
| Mechanical Properties | | |
| Measured thickness (+/-10%) | mm | 0.290 |
| Hardness | Shore D | 25 - 35 |
| Tensile strength | N/mm² | 10 |
| Elongation | % | 5 |
| Physical Properties | | |
| Application temperature | °C | -40 to +500 |
| Density | g/cm³ | > 1.6 |
| Total mass loss (TML) | Ma% | 0.01 |
| Flame rating | UL-94 | V-0 |
| Possible thickness | mm | 0.150 / 0.290 |





Important notes

The data presented in this leaflet are in accordance with the present state of our knowledge. All statements, technical information and recommendations herein are based on tests we believe to be reliable. The customer is thereby not absolved from carefully checking all supplies immediately on receipt. The recommendations made in this catalogue should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. Before using, user shall determine the suitability of the product for its intended use, and the user assumes all risks and liability whatsoever in connection there with. We reserve the right to alter product constants within the scope of technical process or new developments. The recommendations do not absolve the customer from the obligation of investigating the possibility of infringement of third parties right and, if necessary, clarifying the position. Sellers' and manufacturer' only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable either in tort or contract for any loss or damage, direct or incidental, or consequential, including loss of profits or revenue arising out of the use or the inability to use a product. No statement, purchase order or recommendations by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer.

30-06-2014